

L Number	Hits	Search Text	DB	Time stamp
1	21411	(copper cu) with (clad laminate)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2002/10/15 21:58
2	3718	(copper cu) with clad with laminate	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2002/10/15 21:58
3	386	((copper cu) with (clad laminate)) and (hot adj press)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2002/10/15 21:59
4	1	((copper cu) with (clad laminate)) and (hot adj press)) and (recrystallize crystallizable)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2002/10/15 22:37
6	0	((copper cu) with (clad laminate)) and (hot adj press)) and (recrystal crystal)) not ((copper cu) with (clad laminate)) and (hot adj press))	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2002/10/15 22:37
5	62	((copper cu) with (clad laminate)) and (hot adj press)) and (recrystal crystal)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2002/10/15 22:38

L Number	Hits	Search Text	DB	Time stamp
1	21411	(copper cu) with (clad laminate)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2002/10/15 21:58
2	3718	(copper cu) with clad with laminate	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2002/10/15 21:58
3	386	((copper cu) with (clad laminate)) and (hot adj press)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2002/10/15 21:59
4	1	((copper cu) with (clad laminate)) and (hot adj press)) and (recrystallize crystallizable)	USPAT; US-PGPUB; EPO; JPO; DERWENT; IBM_TDB	2002/10/15 22:00